## KONDO PHENOMENA OF STRUCTURAL DEFECTS IN USbTe FERROMAGNET

**Z.Henkie<sup>a</sup>**, **T.Cichorek<sup>ab</sup>**, **R.Wawryk<sup>a</sup>**, **A.Wojakowski<sup>a</sup>**, and **F.Steglich<sup>b</sup>** <sup>a</sup>Institute of Low Temperature and Structure Research, PAS, Wrocaw, Poland <sup>b</sup>Max Planck Institute for the Chemical Physics of Solids, Dresden, Germany

USbTe is a ferromagnet ( $T_C = 123.4$  K) crystallising in tetragonal PbFCl-type structure. Its isostructural compounds UPS and UAsSe, showing low-T turn-up of electrical resistivity, were found to be two-level-system Kondo (i.e. orbital-Kondo, OK) ferromagnets. We have shown previously (phys. stat. sol. (a) **196** (2003) 352) that resistivity along a-axis -  ${}^a\rho(T)$  - for USbTe, unlike that for UPS and UAsSe revealed coherent low-T electronic scattering and unlike typical ferromagnetic metal shows unusually convex shape between 50 K and  $T_C$ .

To explain this unusual behaviour we have measured resistivity along c-axis -  ${}^{c}\rho(T)$  for USbTe and showed that having  ${}^{a}\rho(T)$  and  ${}^{c}\rho(T)$  we can resolve the temperature dependent resistivity of USbTe into components corresponding to particular mechanism of electronic scattering. It occurred that OK effect is responsible for unusual transport properties of USbTe ferromagnet. The OK electronic scattering contributes to the resistivity component  $\rho_K(T)$ . It reaches maximum at  $T^* = 78$  K and goes to zero at the lowest temperatures. Such temperature is assumed to be the Kondo temperature in case of Kondo paramagnetic systems showing transition to coherent electronic scattering and we propose to classify the USbTe as the coherent orbital-Kondo ferromagnet.

Contribution supported by KBN, grant 1PO3B 073 27, and CELTAM

– 13.4 cm –

## Subject category :

1. Correlated Electrons and High Temperature Superconductors

**Presentation mode :** poster

**Corresponding author :** Z.Henkie

Address for correspondence : Z.Henkie

Institute of Low Temperature and Structure Research, PAS, PoBox 1410, 50-950 Wroclaw, Poland

## Email address :

Z.Henkie@int.pan.wroc.pl

9.7 cm